

- Heat Reflective Aluminum Laminated Fiberglass
- Self Wrap And Seal Overlap With High Temperature Adhesive Strip
- Reflects Radiant Heat
- Resists Gasoline And Engine Chemicals
- Cut And Abrasion Resistant



Material Aluminum Laminated Fiberglass	
Grade T6F	
Wall Thickness	
.042" Drawing Number	






Nominal Size	Part #	Wall Thickness ±0.007″	Bulk Box	Box 8x8	Box 6x6	Box 4x4	Available Colors	Lbs/ 10Pcs.
1/4″	T6F0.25SV	0.042″	250	140	100	50	Silver	1.0
3/8″	T6F0.38SV	0.042″	250	90	50	30	Silver	1.5
1/2″	T6F0.50SV	0.042″	250	70	40	25	Silver	2.0
5/8″	T6F0.63SV	0.042″	150	60	35	20	Silver	2.5
3/4″	T6F0.75SV	0.042″	125	50	30	15	Silver	3.0
1″	T6F1.00SV	0.042″	70	30	20	9	Silver	3.5
1 1/4″	T6F1.25SV	0.042″	63	20	10	6	Silver	4.5
1 1/2″	T6F1.50SV	0.042″	40	15	8	4	Silver	5.0
2″	T6F2.00SV	0.042″	24	8	4	2	Silver	6.0

4' Put-Ups -

## Reflective Aluminized Surface Bonded To Insulating Self Wrapping Fiberglass

The newest item in the ThermaShield line of aluminized fiberglass products, T6 is designed for ease of installation when component disassembly isn't practical. Just wrap the pre-formed, split flexible tube around any component and seal the sides with the high temperature adhesive strip to provide protection from hot pipes and engine components.

The highly reflective aluminized exterior, combined with the insulating fiberglass interior, protects delicate wire bundles, cables and lines from damage caused by nearby exhaust pipes, headers or other heat generating components.



HALOGEN

FREE

**FAR-25** 



2100\*

1900\*

1500\*

900\*

600\*

300

300

800

TEMPERATURES

OPERATING



Abrasion Resistance High

**Abrasion Test Machine** 

Taber 5150

Rating \_\_\_\_\_ Non Flammable

2,048°F (1,120°C) Maximum Continuous Mil-I-23053 491°F (255°C)

Melt Point

ASTM D-2117

Minimum Continuous -76°F (-60°C)

## CHEMICAL RESISTANCE

Abrasion Test Load 500g

**Abrasion Test Wheel** 

Calibrase H-18

*Room Temperature* 71°F

*Humidity* 53%

Most Foil Coating Worn Away In Tested Area Of Material **3,500 Test Cycles** 

Braid Worn Through In Both Directions Material Destroyed 6,000 Test Cycles

Pre-Test Weight 18,188.4 mg

Post-Test Weight 16,555.5 mg

Test End Loss Of Mass Point Of Destruction 1,632.9 mg 1=No Effect4=More Affected2=Little Effect5=Severely Affected3=Affected

Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	1
Weak Bases	1
Salts	1
Strong	1
Salt Water 0-S-1926	1
Hydraulic Fluid <i>MIL-H-5606</i>	1
Lube Oil <i>MIL-L-78 08</i>	1
De-Icing Fluid MIL-A-8243	1
Strong Acids	2
Strong Oxidants	2
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen Free	Yes
RoHS	Yes

## O PHYSICAL PROPERTIES

Flammability Rating \_Non Combustible Recommended Cutting \_\_\_\_\_Scissor Colors \_\_\_\_\_\_1 Wall Thickness \_\_\_\_\_\_.042

© 2016 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden.

Techflex product names and logos are registered trademarks of Techflex, Inc., unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 11-15